

CLAIMS

1. A vulcanizable adhesive composition, which comprises 100 parts by weight of phenolxylylene resin or phenolbiphenyl resin, 10 to 1,000 parts by weight of resol-type phenol resin, 0 to 1,000 parts by weight of novolak-type phenol resin, 10 to 1,000 parts by weight of unvulcanized nitrile rubber and 10 to 500 parts by weight of chlorinated polyethylene.

2. A vulcanizable adhesive composition according to Claim 1, as prepared in the form of an organic solvent solution.

3. A vulcanizable adhesive composition according to Claim 1 or 2 for use in vulcanization adhesion between a metal and nitrile rubber or hydrogenated nitrile rubber.

4. An integrated seal parts made up of a metal and nitrile rubber or hydrogenated nitrile rubber, as vulcanization adhered to each other by a vulcanizable adhesive composition according to Claim 1 or 2.

5. An integrated seal parts according to Claim 4 for use as a cryogenic liquid seal.